

# Replacement Element Media

<b>BonDura™</b>	
<b>Appearance</b>	White, uncorrugated
<b>Use</b>	Pleatable filter media
<b>Composition</b>	Spunbond polyester
<b>Area weight (DIN 53884)</b>	270 g/m <sup>2</sup>
<b>Thickness (DIN 53885)</b>	0,58 mm
<b>Air Permeability (DIN53887)</b>	480 m <sup>3</sup> /m <sup>2</sup> .h at 200 Pa
<b>Dimensional stability @ 170°C</b>	N/A
<b>Surface finish</b>	N/A
<b>Additional treatments</b>	N/A
<b>Surface electrical resistance (DIN 54345)</b>	More then 10 <sup>12</sup> Ohm
<b>BIA Category (DIN 60335-2-69)</b>	
<b>Temperature (dry heat)</b>	
<b>Continuous</b>	93°C
<b>Peaks</b>	110°C
<b>Chemical resistance</b>	
<b>Hydrolysis</b>	N/A
<b>Acids</b>	Good
<b>Alkalis</b>	Good
<b>Oxidising Agents</b>	Good
<b>Organic Solvents</b>	Good
<b>Abrasion Resistance</b>	Excellent
<b>Supports Combustion</b>	Yes
<b>Application field</b>	Wide pleat spacing provides excellent particle release. Highly recommended for chemical, food, and industrial processing when product contamination must be minimized. Excellent performance on moist, hygroscopic or agglomerative dust. Chemical processing, Food processing, General industrial

# Replacement Element Media

---



[www.donaldson.com](http://www.donaldson.com)

Humberstone Lane  
Thurmaston  
Leicester LE4 8HP  
England

Tel +44 (0)116 269 6161  
Fax +44 (0)116 269 3028

Email: [IFS-uk@emea.donaldson.com](mailto:IFS-uk@emea.donaldson.com)

Research Park Zone 1  
Interleuvenlaan 1  
B-3001 Leuven (Heverlee)  
Belgium

Tel +32 (0)16 383 970  
Fax +32 (0)16 383 938

Email: [IFS-europe@emea.donaldson.com](mailto:IFS-europe@emea.donaldson.com)