

Replacement Element Media

Ultra-Web® on Spunbond Anti-Static	
Appearance	White, uncorrugated
Use	Pleatable filter media
Composition	Spunbond polyester with nanofiber layer Aluminised
Area weight (DIN 53884)	260 g/m ²
Thickness (DIN 53885)	0,61 mm
Air Permeability (DIN53887)	420 m ³ /m ² .h at 200 Pa
Dimensional stability	N/A
Surface finish	Aluminised
Additional treatments	N/A
Surface electrical resistance (DIN 54345)	Less then 10 ⁴ Ohm
BIA Category (DIN 60335-2-69)	
Temperature (dry heat)	
Continuous	65°C
Peaks	80°C
Chemical resistance	
Hydrolysis	N/A
Acids	Good
Alkalis	Good
Oxidising Agents	Good
Organic Solvents	Good
Abrasion Resistance	Excellent
Supports Combustion	Yes
Application field	Wide pleat spacing provides excellent particle release. Highly recommended for chemical, food, and industrial processing when product contamination must be minimized. Excellent performance on moist, hygroscopic or agglomerative dust. High filtration efficiency on very fine particulate of <1 micron. Chemical processing, Food processing, General industrial

Replacement Element Media



www.donaldson.com

Humberstone Lane
Thurmaston
Leicester LE4 8HP
England

Tel +44 (0)116 269 6161
Fax +44 (0)116 269 3028

Email: IFS-uk@emea.donaldson.com

Research Park Zone 1
Interleuvenlaan 1
B-3001 Leuven (Heverlee)
Belgium

Tel +32 (0)16 383 970
Fax +32 (0)16 383 938

Email: IFS-europe@emea.donaldson.com